



REEGROUT EG1040

Pourable Epoxy Grout



USES

Reegrout EG1040 is suitable for use where a high strength, fast curing flow-applied grout is required. Ideal situations include grouting of holding down bolts and fixing, machine beds, holes and cavities in concrete etc.

DESCRIPTION

Reegrout EG1040 is based on a blend of epoxy resins, curing agents and selected fine fillers. Supplied in pre-weighed containers ready for mixing on site. The mixed material provides a free flowing, self-levelling grout system.

ADVANTAGES

Rapid strength gain - No shrinkage - High bond strength

APPLICATION GUIDELINES

SURFACE PREPARATION

New concrete should have an RH% of 75% or less. The substrate should be clean, free from laitance, oil, grease or other agents, which may impair adhesion.

MIXING INSTRUCTIONS

IT IS IMPERATIVE THAT THE MIXING IS CARRIED OUT IN THE RESIN CONTAINER. Reegrout EG1040 is supplied in pre-weighed containers and no addition of solvents or aggregates should be carried out on site. All of the hardener should be added to the resin and mixed by drill with mixing attachment for 2-3 minutes or until a uniform colour is achieved. Pour the mixed material onto the prepared surface ensuring complete filling of the hole or void.

TECHNICAL DATA

Usable Life @ 20°C	45 Minutes
Compressive Strength	43 N/mm ²
Flexural Strength	78 N/mm ²
S.G.	1.5
Shelf Life in sealed container	12 Months
Store away from Food, Drinks, Animals and Children	

REEGROUT EG1040

Pourable Epoxy Grout

STORAGE, MIXING & APPLICATION

The storage, mixing and application conditions can affect the quality of the finished product. Please refer to our Information Data Sheet reference TD300.

CLEANING

All tools, etc. should be cleaned with Reepol Thinners RC4 immediately after use. For hands - soap and water.

PACKAGING

Pack Size 5.00kg - approx. 3.3 Ltrs
Coverage 0.003m³/3.3 Ltrs

Coverage is given as a guide only as the exact coverage will vary from floor to floor.

HEALTH & SAFETY

It is recommended that barrier creams, gloves and protective clothing are used when using Reegrout EG1040. If eyes are affected wash with copious amounts of water and seek medical advice. For hands - wash with soap and water. For full details refer to C.H.I.P data sheet.



**Reepol Chemical Building
Products Limited.**

Court Works, Bridgnorth Road,
Madeley, Telford, Shropshire TF74JB.

T 01952 588575
F 01952 587886
E sales@reepol.com
W www.reepol.com

This information is given to the best of our knowledge but without obligation. We reserve the right to change the product for technical reasons and also to make changes to the specifications. This technical information becomes void as soon as a new edition appears.

Materials are supplied subject to our Terms and Conditions - copies available on request.